

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
24 July 2003 (24.07.2003)

PCT

(10) International Publication Number  
**WO 03/059969 A1**

(51) International Patent Classification<sup>7</sup>: **C08F 214/26**

(21) International Application Number: PCT/JP03/00330

(22) International Filing Date: 17 January 2003 (17.01.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
10/046,702 17 January 2002 (17.01.2002) US

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier application:  
US 10/046,702 (CIP)  
Filed on 17 January 2002 (17.01.2002)

(71) Applicant (for all designated States except US): **DAIKIN INDUSTRIES, LTD.** [JP/JP]; Umeda Center Bldg., 4-12, Nakazakinishi 2-chome, Kita-ku, Osaka-shi, Osaka 530-8323 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KONO, Hideki**

[JP/JP]; c/o DAIKIN INDUSTRIES, LTD., Yodogawa Plant., 1-1, Nishihitotsuya, Settsu-shi, Osaka 566-8585 (JP). **HIRAO, Takayuki** [JP/US]; c/o DAIKIN AMERICA, INC., 20 Olympic Drive, Orangeburg, NY 10962 (US). **GEORGE, Lin** [US/US]; c/o DAIKIN AMERICA, INC., 20 Olympic Drive, Orangeburg, NY 10962 (US). **FUKUDA, Kazuyuki** [JP/JP]; c/o DAIKIN INDUSTRIES, LTD., Yodogawa Plant., 1-1, Nishihitotsuya, Settsu-shi, Osaka 566-8585 (JP).

(74) Agents: **YASUTOMI, Yasuo** et al.; Chuo BLDG., 4-20, Nishinakajima 5-chome, Yodogawa-ku, Osaka-shi, Osaka 532-0011 (JP).

(81) Designated States (*national*): CN, US.

(84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR).

**Published:**

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: FEP PELLET

(57) Abstract: An FEP pellet having a volatile content of 0.2 % by weight or less. The FEP pellet satisfies the following requirements (i) and (ii) when used to form an insulating material coating a core wire by extrusion coating at a coating speed of 2,800 ft/min.: (i) an adhesive strength between the insulating material and said core wire of 0.8 kg or more; and (ii) an average number of cone-breaks in the insulating material of one or less per 50,000 feet of the coated core wire.

501,978



WO 03/059969 A1